

### DIMENSIONS

FORMAT	Deluxe	
Width	192	mm
Length	1257	mm
Number of panels per pack	9	
m <sup>2</sup> per pack	2.172	m <sup>2</sup>
Bevels	4V	
Thickness	8	mm
Tongue and groove	FitXpress	

### FACTORY WARRANTY

	METHOD	PARAMETERS	Balterio VALUES	
Usage class	EN 13329		Class	21-22-23/31-32
CE	EN 14041	Notified body	NB0766 EPH Dresden	
Warranty	Residential use	See warranty conditions	25	years
	Commercial use	See warranty conditions	5	years

### GENERAL DATA (ACCORDING TO EN 13329)

	METHOD	PARAMETERS	NORM REQUIREMENTS	Balterio VALUES		
Wear resistance	EN 13329		≥ 4000 cycles	≥ 4000	cycles	
Wear class	EN 13329		AC4			
Impact resistance	EN 13329	Small ball	≥ 12N	≥ 12N		
		Big ball	≥ 750mm	≥ 750mm		
Scratch resistance	EN 438-2, 25		Charge ≥ 3N	Charge	≥ 5N	
Effect of a castor chair	ISO 4918 (with underlay)		25000 cycles	No change		
Thickness swelling	ISO 24336	After 24h immersion at 20°C	≤ 18%	≤ 18%		
Locking strength	ISO 24334	F10,2 long side	≥ 1 kN/m	≥ 1	kN/m	
		Fmax long side		≥ 1	kN/m	
		Fs0,2 short side	≥ 2 kN/m	≥ 2	kN/m	
		Fmax short side		≥ 2	kN/m	
Effect of a furniture leg	EN 424		No damage shall be visible, when tested with foot type 0	No visible damage		
Surface soundness	EN 13329	N/mm <sup>2</sup>	≥ 1,25	≥ 1,50		
Static indentation	EN 433		residual indentation ≤ 0,05 mm	No visible change		
Resistance to staining	EN 438	Group 1,2	Class 5	Class	5	
		Group 3	Class 4	Class	4	
General appearance	EN 13329	Height differences	≤ 0,15 mm	≤ 0,10 mm		
		Opening between joints	≤ 0,20 mm	≤ 0,10 mm		
		Cupping in the length	concave	≤ 0,50%	≤ 0,50%	
			convex	≤ 1,00%	≤ 1,00%	
		Cupping in the width	concave	≤ 0,15%	≤ 0,15%	
convex	≤ 0,20%		≤ 0,20%			
Dimensional variations after changes in relative humidity	EN 13329	δl	δl average ≤ 0,9 mm	≤ 0,9 mm		
		δw	δw average ≤ 0,9 mm	≤ 0,9 mm		
Light fastness	EN ISO 4892-2:2006/A1:2009 procedure B - cycle 5	grey reference	Class ≥ 4	Class	4	



#### OTHER TECHNICAL DATA

	METHOD	PARAMETERS	NORM REQUIREMENTS	Balterio VALUES
Impact sound reduction	ISO 712/2	On a Balterio underlay		$\Delta L_w \approx 20$ dB (Depending on used underlay)
Burning cigarette	EN 438-2,30		Class 4	Class 5

#### ENVIRONMENT, SAFETY & HEALTH

	METHOD	PARAMETERS	NORM REQUIREMENTS	Balterio VALUES
Formaldehyde emission	EN 717-1	ppm	$E1 \leq 0,1$	$< 0,01$
Anti-static	EN 1815		$\leq 2,0$ kV	$\leq 2,0$ kV
Reaction to fire	EN 13501-1	Class		Cfl-s1
Thermal resistance	EN 12996:2001	$m^2K/W$		0.055 $m^2K/W$
Floor heating		On a Balterio underlay	See special instructions	Suitable
Slip resistance	EN 13893	$\mu$	$\mu \geq 0,30$	DS: $\mu \geq 0,30$

#### CERTIFICATES

U-zeichen	Z-156.606-996
AFFSET	A+
PEFC	PEFC/07-32-37
M1	
EU Ecolabel	SE/035/001

